

MirroFlex[™] Structures Technical Information

GENERAL INFORMATION:

Description

- MirroFlex™ Structures are decorated thermoplastic sheets with high impact resistance and are available in a wide variety of patterns and colors. They can be used as a value-added product in areas that vertical grade High Pressure Laminates (HPL) are typically used.
- Unlike HPL, MirroFlex™ Structures can easily be cut to size with razor knives or scissors. It can also be applied to many substrates with pressure sensitive adhesive strips and be used for retrofits and DIY applications.
- Size 4' x 8' x .032" (1220 x 2440 x .8 mm). This is a dimensional product, so actual thickness varies by pattern.
- Most product ships with clear protective film or with TuffCote™.
- UPS Shippable

<u>Applications</u>

Commercial Market Uses:

Office - desks, storage cabinets, reception, etc.

Education – cabinets, high impact areas

Healthcare – furniture, equipment, high impact areas

Hospitality – restaurants, bar & counter fronts, hotels/motels

Store & Bank Fixtures

Interior Doors, Kiosk Fronts & Elevator Cab Interiors-including high impact areas

Wall Panels & Signage

Bathroom Enclosures (Only when MirroFlex Tub & Shower Wall Panels™ are used)

Recreational Market Uses:

Boat Interiors

Coach Interiors

Residential Market Uses:

Occasional Furniture – tables, cabinets, etc.

Novelty and Juvenile Furniture

DIY and Renovations

ATI Decorative Laminates (800) 849-1320 www.atilaminates.com

PHYSICAL PROPERTIES:

N/A

TECHNICAL PROPERTIES:

PROPERTY	TEST METHOD	TYPICAL VALUE			
Fire Retardant	ASTM E-84	Class A			
QUV		Minimum 100 hours			
Solvent Resistance		50 MEK			
Llumidity		12 hrs 96-100% RH @			
Humidity		40 degrees C on MDF			
MEK Double Rubs/Crockmeter		Withstands 70 cycles			
Impact Resistance	ASTM D5420	>2 inch lbs per mill of			
Impact Resistance	A31101 D3420	thickness			
Abrasion Resistance –	ASTM D1044				
Patina with TuffCote	Taber Abrader 5130	4,700*			
Argent Finishes	500 gm weight	5,000*			
EccoFlex Paintable	CS-10 Calibrase wheel	1,000*			

^{*}no sign of wear

ATI Decorative Laminates (800) 849-1320 www.atilaminates.com

ADDITIONAL INFORMATION:

Stain Resistance Properties

Stain Resistance Testing		Group 1		Group 2		Group 3		Group 4		Group 5		Group 6	
#	Materials	24 Hrs	7 Day										
1	Wesson Oil	N	N	N	N	N	N	N	N	N	S	N	N
2	Household Ammonia	N	N	N	N	N	N	N	N	S	S	N	Ν
3	409 all purpose cleaner	N	N	S	S	N	N	N	N	N	N	N	Ν
4	"Tide" laundry detergent	N	N	N	N	N	N	N	N	N	N	N	Ν
5	Isopropyl Alcohol	N	N	S	S	N	N	N	N	N	N	N	Ν
6	Clorox	N	N	S	М	L	L	L	L	L	L	N	N
7	Grape Juice	N	N	N	N	N	N	N	N	N	N	N	N
8	Orange Juice Concentrate	N	N	N	N	N	N	N	N	N	N	N	N
9	Coffee	N	N	N	N	N	N	N	N	N	S	N	N
10	Mustard	N	N	N	N	N	N	N	N	S	S	N	Ν
11	Ketchup	N	N	N	N	N	N	N	N	N	N	N	Ν
12	Red wine	N	N	N	N	N	N	N	N	N	N	N	Ν
13	Coca-Cola	N	N	N	N	N	N	N	N	N	N	N	Ν
14	Water	N	N	N	N	N	N	N	N	N	N	N	Ν
15	Black crayon	N	N	N	N	N	N	N	N	N	N	L	L
16	Lipstick	N	N	N	N	N	N	N	N	N	N	L	L
17	Pine-Sol	N	N	S	S	N	N	N	N	N	N	N	N
18	Vinegar	N	N	N	N	N	N	L	L	N	N	N	N
19	Steel Wool	N	N	N	N	N	N	N	N	N	N	N	N
20	Tea	N	N	N	N	N	N	N	N	N	N	N	N
21	Windex® Surface Cleaner	N	N	N	N	N	N	N	N	N	N	N	N
22	Scotch-Brite® w/Soap	N	N	N	N	N	N	N	N	N	N	N	N

Group 1 - Patina, Brushed Aluminum, Paintable, Mirror Red, Argents

Group 2 - Woodgrains

Group 3 - Mirror, Mirror Blue

Group 4 - Mirror Gold

Group 5 - Brushed Copper

Group 6 - EccoFlex Paintable

N = no change

S = slight change

M = medium change

L = large change