



COMMERCIAL TESTING COMPANY

1215 South Hamilton Street • Dalton, Georgia 30720
Telephone (706) 278-3935 • Facsimile (706) 278-3936

Standard Method of Test for Surface Burning Characteristics of Building Materials

ASTM E84-11a

MirroFlex FR PETG Opaque Wall Panel- Bronze

Report Number 12-10198

Test Number 4263-5066-1012R

September 02, 2019

Advanced Technology, Inc.
Greensboro, North Carolina

Commercial Testing Company

(Authorized Signature)

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. The test results presented in this report apply only to the samples tested and are not necessarily indicative of apparent identical or similar materials. Sample selection and identification were provided by the client. A sampling plan, if described in the referenced test procedure, was not necessarily followed. This report, or the name of Commercial Testing Company, shall not be used under any circumstance in advertising to the general public.

TESTED TO BE SURE®
Since 1974

INTRODUCTION

This report is a presentation of results of a surface flammability test on a material submitted by Advanced Technology, Inc., Greensboro, North Carolina.

The test was conducted in accordance with the ASTM International fire test response standard E 84-IIa, *Surface Burning Characteristics of Building Materials* sometimes referred to as the Steintunnel test. This test is applicable to exposed surfaces such as walls and ceilings. The test is conducted with the specimen in the ceiling position with the surface to be evaluated exposed face down to the ignition source. The ASTM E 84 test method is the technical equivalent of NFPA No. 255 and UL No. 723.

This standard is used to measure and describe the response of materials, products, or assemblies to heat and flame under controlled conditions, but does not by itself incorporate all factors required for fire- hazard or fire-risk assessment of materials, products, or assemblies under actual fire conditions.

PURPOSE

The purpose of the test is to provide only the comparative measurements of surface flame spread and smoke development of materials with that of select grade red oak and fiber-reinforced cement board, Grade II, under specific fire exposure conditions. The test exposes a nominal 24-foot long by 20-inch wide test specimen to controlled airflow and flaming fire adjusted to spread the flame along the entire length of a red oak specimen in 5.50 minutes. During the 10-minute test duration, flame spread over the specimen surface and density of the resulting smoke are measured and recorded. Test results are calculated relative to red oak, which has an arbitrary rating of 100, and fiber-reinforced cement board, Grade II, which has a rating of 0.

The test results are expressed as the Flame Spread Index and Smoke Developed Index. The Flame Spread Index is defined in ASTM E 176 as "a number or classification indicating a comparative measure derived from observations made during the progress of the boundary of a zone of flame under defined test conditions." The Smoke Developed Index, a term specific to ASTM E 84, is defined as "a number or classification indicating a comparative measure derived from smoke obscuration data collected during the test for surface burning characteristics." There is not necessarily a relationship between the two measurements.

The method does not provide for measurement of heat transmission through the surface tested, the effect of aggravated flame spread behavior of an assembly resulting from the proximity of combustible walls and ceilings or classifying a material as noncombustible solely by means of a Flame Spread Index.

The zero reference and other parameters critical to furnace operation are verified on the day of the test by conducting a 10--minute test using 1/4-inch fiber-reinforced cement board, Grade II. Periodic tests using NOFMA certified 23/32-inch select grade red oak flooring provides data for the 100 reference.

TEST SAMPLE

The test sample, selected by the client, was identified as MirroFlex FR PETG Opaque with CBS1000 VF Formed Tile, a decorative tile with a mirror finish. The material was conditioned to equilibrium in an atmosphere with the temperature maintained at $71 \pm 2^{\circ}\text{F}$ and the relative humidity at 50 ± 5 percent. For testing, six pieces of the material, each measuring 2 feet wide by 4 feet in length, were free laid over a 2-inch hexagonal wire mesh supported by 1 / 4-inch diameter steel rods spanning the ledges of the tunnel furnace at 24-inch intervals. This method of auxiliary sample support is described in Appendix XI of the E 84 standard, Guide to Mounting Methods, Sections XI.1.2.2(a) and XI.1.2.3.

TEST RESULTS

The test results, calculated based on observed flame propagation and the integrated area under the recorded smoke density curve, are presented below. The Flame Spread Index obtained in E 84 is rounded to the nearest number divisible by five. Smoke Developed Indices are rounded to the nearest number divisible by five unless the Index is greater than 200. In that case, the Smoke Developed Index is rounded

to the nearest 50 points. The flame spread and smoke development data are presented graphically at the end of this report.

Test Specimen	Flame Spread Index	Smoke Developed
Fiber-Reinforced Cement Board,	0	0
Grade II Red Oak Flooring	100	100
MirroFlex FR PETG Opaque with Bronze VF Formed Wall Panel	5	175

OBSERVATIONS

Specimen ignition over the burners occurred at 0.25 minute. The surface flame spread was observed to a maximum distance of 0.81 feet beyond the zero point at 1.07 minutes. The maximum temperature recorded during the test was 537°F.

CLASSIFICATION

The Flame Spread Index and Smoke Developed Index values obtained by ASTM E 84 tests are frequently used by code officials and regulatory agencies in the acceptance of interior finish materials for various applications. The most widely accepted classification system is described in the National Fire Protection Association publication NFPA 101 *Life Safety Code*, where:

Class A	0-25 Flame Spread Index	0-450 Smoke Developed Index
Class B	26-75 Flame Spread Index	0-450 Smoke Developed Index
Class C	76-200 Flame Spread Index	0-450 Smoke Developed Index

Class A, B, and C correspond to Type I, II, and III respectively in other codes. They do not preclude a material being otherwise classified by the authority of jurisdiction.

ASTM E 84 TEST DATA

Client: Advanced Technology, Inc.

Test Number: 4263-5066-1012R

Date: September 02, 2019

Material Tested: MirroFlex FR PETG Opaque Bronze VF Formed Wall Panel

Test Results:

Time to Ignition = 00.25 minutes

Maximum Flamespread Distance = 00.81 feet

Time to Maximum Spread = 01.07 minutes

Flame Spread Index = 5

Smoke Developed Index = 175

