

**PRODUCT:** PF-020-X0-00-00 X=.375 REV072621

**PRODUCT DESCRIPTION:** Compressed partition fiber blend

**FIBER**

| Physical Property     | Description - Value | Tolerance |
|-----------------------|---------------------|-----------|
| Material              | FR Fiber blend      |           |
| Thicknesses (nominal) | 9.5mm               | +/- 1mm   |
| Color                 | White               |           |
| Service Temperature   | -40 °F – 175 °F     |           |

**ABSORPTION COEFFICIENT, NRC and SAA to ISO 354**

| Frequency | Sound Absorption Coefficient (1") |
|-----------|-----------------------------------|
| (Hz)      | $\alpha_s$                        |
| 100       | 0.03                              |
| 125       | 0.07                              |
| 160       | 0.07                              |
| 200       | 0.08                              |
| 250       | 0.13                              |
| 315       | 0.17                              |
| 400       | 0.20                              |
| 500       | 0.23                              |
| 630       | 0.31                              |
| 800       | 0.34                              |
| 1000      | 0.41                              |
| 1250      | 0.45                              |
| 1600      | 0.50                              |
| 2000      | 0.54                              |
| 2500      | 0.58                              |
| 3150      | 0.61                              |
| 4000      | 0.68                              |
| 5000      | 0.91                              |
| NRC       | 0.33                              |
| SAA       | 0.33                              |

\*THE VALUES PRESENTED ARE TYPICAL AND ARE NOT INTENDED FOR SPECIFICATION PURPOSES. This information is provided without warranty, representation, inducement or license of any kind. INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR USE OR PURPOSE, except that it is accurate to the best of Technicon Industries' knowledge or obtained from sources believed by Technicon Industries to be accurate, and Technicon Industries does not assume any legal responsibility for the use or reliance upon same. Customers are encouraged to conduct their own tests for suitability and conformance.

**ISO 354:2003 - Sound Absorption in Reverb Room**

**Test ID: 354-072621-1**

**Product Description: PF-020-X0-00-00**

**Thickness: .375 inch, Mounting A**

