



PRODUCT DATA SHEET

Digital High-Impact Polystyrene

Resin Property	Unit	Values	ASTM Method
Specific Gravity	g/cm ³	1.04	D792
Vicat Softening Point	°F	212	D1525
Heat Deflection Temperature @66psi	°F	183	Internal
Rockwell Hardness	“L” scale	50	D785
Notched Izod Impact @73°F	ft-lb/in	2.6	D256
Tensile Modulus	psi	270,000	D638
Flexural Modulus	psi	270,000	F790

DISCLAIMER:

All listed technical data are typical values intended for your guidance. Final testing and fitness for use are determined by the end customer and intended use. ATI Laminates encourages customers to conduct their own test to determine physical properties.